

# Dekguard Primer



constructive solutions

**Silane Siloxane based penetrating and film forming primer**

## Uses

- Protects concrete from ingress of water and chloride ions
- Excellent water repellency
- Suitable for both new and old concrete
- Single part – easy to use

## Description

Dekguard Primer is a penetrating, primer which is supplied as a clear liquid and is based on an silane-siloxane dissolved in a penetrating organic carrier. The primer is reactive and capable of producing a chemically-bound hydrophobic barrier, thus inhibiting the passage of water and water-borne contaminants. A thin surface film is produced which consolidates and stabilises porous substrates.

## Instructions for use

The primer will penetrate and "stabilise" the substrate. The depth of penetration of the primer, and thus its coverage rate, are determined by substrate profile, porosity and general condition. Hence for low permeability concretes, primer penetration will be low and area covered per litre will be high. It is thus recommended that a general coverage rate of 4m<sup>2</sup>/litre be observed, noting that this may change according to substrate condition.

Any areas of glass should be masked. Plants, grass, joint sealants, asphalt and bitumen-painted areas should be protected during application.

The primer is best applied by using portable spray equipment e.g. knapsack-type. A uniform surface appearance (sheen) should be apparent when the required rate of application rate has been achieved. If any matt, porous patches remain, then a further application of Dekguard Primer should be made.

If in any doubt regarding substrate priming, contact the local Fosroc office.

## Al Gurg Fosroc LLC

Post Box 657, Dubai  
United Arab Emirates

Telephone:  
(+9714) 2858606

fax:  
(+9714) 2859649

email:  
[agf@fosroc.com](mailto:agf@fosroc.com)

[www.fosroc.com](http://www.fosroc.com)

Registered Office: 215 Community, Street No. 13, Nad Al Hamar Road, Al Ramool Industrial Estate, Rashidiya, Dubai





*constructive solutions*

### **Application**

The correct application rates and overcoating times should be observed, in order to obtain the complete benefits of the protective properties, except where substrate condition dictates different application rates for the primer.

#### **Dekguard Primer**

Number of coats	:	1
Theoretical application rate per coat	:	4m <sup>2</sup> /ltr
Overcoating time	:	@ 20°C 2 hours and @ 35°C 1 hour

Under no circumstances should the primer be overcoated until the surface is properly dry.

### **Limitations**

- Should not be used at temperatures below 4°C.
- Concrete coated with sealers, coating or curing membranes must be stripped to provide an open surface.