



Fosroc Nitotile LM Grout

Latex modified, cementitious grout for ceramic tiles

Uses

As a grout for tile joints in:

- Kitchens
- Bathrooms
- Shower stalls
- Swimming pools

Advantages

- Low cost service life-mould resistant, tropical grade suits Middle East working conditions
- Easy to apply - thixotropic, non-slump grout
- Water resistant - can be used in submerged conditions
- Available in a range of attractive colours

Description

Nitotile LM Grout is supplied as a two component pack, comprising separate powder and liquid components, which requires only the on-site addition of clean water. It readily blends to produce a smooth creamy paste which, when set, is water and mould resistant. Nitotile LM Grout is used in conjunction with Nitotile tile adhesives.

Standard Compliance

Nitotile LM Grout conforms to EN 13888 of Cementitious tile grouts.

Properties

	EN13888	Test result
Compressive Strength (N/mm ²)		
(EN12808-3)	: > 15	> 20
Flexural Strength (N/mm ²)		
(EN12808-3)	: > 2.5	> 5
Water absorption (g)		
(EN12808-5)		
after 30 minutes	: < 5	< 2
after 240 minutes	: < 10	< 4
Abrasion resistance (mm ³)		
(EN12808-2)	: < 2000	< 600
Shrinkage (mm/m)		
(EN12808-4)	: < 3	< 2.5

Instructions for use

Preparation

All tiles must be securely fixed in place and thoroughly cleaned before Nitotile LM Grout is applied. The gap between tiles should not exceed 6 mm.

Mixing

A slow speed drill fitted with a suitable mixing paddle and mixing vessel of minimum 30 litre capacity are recommended.

Measure out 6.4 litres of clean water into the mixing vessel and add the liquid component, stir thoroughly until dispersed. With the mixing paddle in operation, add the powder component to the mix and continue mixing for 5 minutes until a uniform, lump-free consistency is achieved. Allow to stand for 10 minutes prior to use.

Application

Apply Nitotile LM Grout to the spaces between the tiles using a sponge or a small piece of soft cloth. Work the mixture into the joints and around the edges.

Remove surplus material from the face of the tiles with a dry cloth and run the tip of a gloved finger or suitable rounded tool along the grout to level it off and form a profile.

When the grout is dry, clean the tiles with a damp sponge to remove any excess material. It is advisable to remove uncured grout from textured tiles prior to setting, failure to do so may result in difficulty in removal.

Cleaning

Nitotile LM Grout should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Limitations

Nitotile LM Grout should not be used when the temperature is below 5°C and falling. The product should not be exposed to moving water during application. If any doubts arise concerning temperature or substrate conditions, consult your local Fosroc office.

Fosroc Nitotile LM Grout

Estimating

Supply

Nitotile LM Grout powder : 20 kg bags

Nitotile LM Grout liquid : 0.8litre

Yield

Nitotile LM Grout : 15 ltrs per bag

Storage

Shelf life

Nitotile LM Grout has a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperature and / or high humidity conditions the shelf life may be reduced to 4 to 6 months.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Precautions

Health and safety

Nitotile LM Grout is cement based. Care should be taken to avoid inhalation of dust and contact with eyes. All cement based products, when mixed or damp release alkalis which can be harmful to the skin.

Additional Information

Nitotile LM Grout is part of a range of Fosroc tile adhesives and tile grouts.

Fosroc manufactures a wide range of complementary products which include:

- Waterproofing membranes & waterstops
- Joint sealants & filler boards
- Cementitious & epoxy grouts
- Specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following:

- Hand-placed repair mortars
- Spray grade repair mortars
- Fluid micro-concretes
- Chemically resistant epoxy mortars
- Anti-carbonation/anti-chloride protective coatings
- Chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: agf@fosroc.com

Regional offices

Abu Dhabi, Al Gurg Fosroc
Bahrain, YBA Kanoo
Kuwait, Boodai
Oman, Al Amana
Qatar, Tadmur

telephone: 673 1779
telephone: 17738200
telephone: 4817618
telephone: 24815080
telephone: 4432365

fax: 673 1449
fax: 17732828
fax: 4832124
fax: 24817554
fax: 4419517

email: abudhabi@fosroc.com
email: bahrain@fosroc.com
email: kuwait@fosroc.com
email: oman@fosroc.com
email: qatar@fosroc.com

Al Gurg Fosroc LLC

Post Box 657, Dubai
United Arab Emirates

www.fosroc.com

