

# GLENIUM<sup>®</sup> ACE 415

**A new generation high-performance polycarboxylic ether based superplasticizer for the Precast industry.**

## Description and field of application

GLENIUM ACE (Admixture Controlled Energy) consists of a range of innovative superplasticizers based on newly developed polycarboxylic ether polymers. The particular molecular configuration of GLENIUM ACE 415 accelerates the cement hydration by exposing increased surface of the cement grains to react with water. As a result, it is possible to obtain earlier development of the heat of hydration, rapid development of the hydration products and, as a consequence, higher strengths at very early age. The polymer structure of GLENIUM ACE 415 is specially designed to improve the rheology of precast concrete, making it very flowable and low viscous even at very low water/cement ratios, without increasing stickiness. Robustness is a distinctive feature of the precast concrete produced with GLENIUM ACE 415.

## Fields of application

GLENIUM ACE 415 is suitable for making precast concrete elements with normal, high slump or highly-fluid concrete without segregation with a low water cementitious ratio, consequently, high early and final strengths are achieved. GLENIUM ACE 415 can also be used in combination with RheoMATRIX for producing advanced self-compacting concrete such as Smart Dynamic Concrete (SDC, latest type SCC), without the aid of vibration giving economic, ecological and ergonomic precast production.

## Features & Benefits

GLENIUM ACE 415 offers the following benefits for the precast concrete industry:

- Production of highly flowable, robust self-compacting concrete having a low water cement ratio along with an optimal rheology.
- Enhanced robustness and consistency in concrete quality with low stickiness.
- Environmentally friendly, CO<sub>2</sub> reduced mix-design optimization.
- Improved surface appearance.
- Durable precast concrete elements as per EN 206-1.
- Elimination or reduction of the energy required for placing, compaction and curing.
- Optimization of the curing cycles by reducing curing time or curing temperature.
- Increased productivity.

## Packaging

GLENIUM ACE 415 is available in bulk or in 210 litre drums.

## Standards

EN 934-2 and ASTM C494 Type A & F.

## \*Technical data/Typical properties

Appearance and Form	Whitish to light Brownish liquid
Specific gravity @ 25°C	1.030 typical
pH-value @ 25°C	5 - 7
Chloride ion content	"Chloride Free" to EN 924-1
Alkali content (Na <sub>2</sub> O equivalent %)	< 3%

# GLENIUM<sup>®</sup> ACE 415

## Directions for use

GLENIUM ACE 415 is a liquid admixture to be added to the concrete during the mixing process. The best results are obtained when the admixture is added to the mixing water that is used for the concrete mix after all the other components are already in the mixer and after the addition of at least 80% of the total water.

Avoid adding the admixture to the dry aggregates. After adding GLENIUM ACE 415 admixture provide enough mixing time to secure a homogenous dispersion. Continue mixing and adjust the water content to obtain the required workability.

## Dosage rate

The recommended dosage rate is 0.5 to 2.0 liters per 100 kg of the cementitious binder.

Other dosages may be used in special cases according to specific production conditions. In this case please consult our Technical Services Department.

## Compatibility

GLENIUM ACE 415 is compatible and recommended for use with:

- RheoMATRIX to modify the viscosity of SCC mixes.
- MICRO-AIR, air entraining admixture, to improve freeze-thaw resistance (exposure class XF1 to XF4, EN 206-1)
- RHEOFINISH, demoulding agent for easy formwork removal and improved finish.
- MASTERKURE, curing compound for highly efficient water retention and friendly use.

GLENIUM ACE 415 is **not compatible** with all admixtures of RHEOBUILD series.

## Storage

GLENIUM ACE 415 must be stored in a place where the temperature does not drop below 5°C. In case of freezing, warm up and homogenise the admixture solution before using. If stored in unopened containers according to manufacturer's instructions, the shelf life is 12 months.

## Handling & storage

No special requirements must be observed while the product is used. Protection gloves and glasses are recommended. Do not eat, drink or smoke during the application. GLENIUM ACE 415 is not-flammable, non-toxic or irritant and are not subject to special transport requirements.

## Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.



The Chemical Company

# GLENIUM<sup>®</sup> ACE 415

## Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

12/2009 BASF\_CC-UAE

\* Properties listed are based on laboratory controlled tests.

---

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

**As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.**

---

**BASF Construction Chemicals UAE LLC**

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.basf-cc.ae

