

RheoFIT[®] 762

Block-admixture for improving concrete

Description

RheoFIT[®] 762 is a plasticiser liquid admixture with air entraining properties. Designed for use in no-slump concrete, it is ideally suited for factory-line concrete production such as block making. RheoFIT[®] 762 assists in the manufacture of a more uniform and predictable concrete. Chloride free RheoFIT[®] 762 may also be used in dry pack, standard and light weight concrete production.

FIT 4 VALUE:

RheoFIT[®] 762 is a key component to BASF's FIT 4 VALUE concept.

FIT 4 VALUE considers the four elements essential for MCP Manufactures:

1. FIT for Economics
2. FIT for Performance
3. FIT for Aesthetics
4. FIT for Durability

Here, FIT means meeting every requirement for economics, performance, aesthetics and durability.

Advantages

- Less wear of moulds.
- Improved structure.
- Improved cohesion.
- Reduced water absorption.
- Increased strength.
- Applicable for all Portland and Slag cements.
- Reduced efflorescence.

Packaging

RheoFIT[®] 762 is available in bulk or in 210 litre drums.

Dosage

As a starting base for factory trials a rate between 325ml/100kg and 650ml/100kg is recommended. Local production conditions and material types may necessitate dosages outside this range. Please consult your BASF Construction Chemicals representative for further advice.

Application

- Mix the aggregates, the cement and 75% of the mixing water.
- Add the RheoFIT[®] 762 together with the rest of the mixing water.
- After all ingredients are added continue mixing for 60 to 90 seconds.

*Typical properties

Form:	liquid soluble in water
Colour:	dark brown
pH:	6.0
Specific Gravity	1.185 at 25°C
Chloride content:	Nil to BS 5075: 1982
Viscosity at 25°C:	50 cps
Solids content	Approx. 35%

Standards

EN 934-2 Table 2

Health and safety

Avoid contact with eyes and prolonged contact with skin. During application always wear gloves and appropriate clothing to minimise contact. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Should skin contact occur, wash immediately with soap and water. Seek the advice of a physician should symptoms persist.



The Chemical Company

RheoFIT[®] 762

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is up to 2 years when stored as above. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

10/2006 BASF_CC-UAE revised 04/2008

* Properties listed are based on laboratory controlled tests.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

Fax: +971 4 8851002

www.basf-cc.ae

