









Sika Waterbars®

Construction

Product Description	Flexible Soft PVC-Waterbars to seal construction and expansion joints in concrete structures. Sika Waterbars® are available in different sizes and types, depending on their use.	
Uses	Sika Waterbars® are used to seal construction and expansion joints in water retaining structures such as reservoirs, water towers, dams, spillways, canals, swimming pools, sewage tanks etc... as well as to keep water out of concrete structures such as basements, underground car parks, tunnels, subways retaining walls etc...	
Advantages	<ul style="list-style-type: none"> ■ Multirib sections of the tortuous path principal. ■ High quality PVC for long durability. ■ Suitable for high water pressure. ■ Easy to install (clip fastening), easy to weld on site. ■ Many different sizes and types available, depending on their use ■ Factory produced cross sections available. 	
Standards/Approvals	Sika Waterbars® have been tested in accordance to: <ul style="list-style-type: none"> ■ BS. 2571 ■ DIN 18541, Part 2 ■ US. corps of Engineers: CRD-C 572 ■ ASTM D-412 & ASTM D-638 	
Product Data		
Colour	For construction joints: grey. For expansion joints: yellow	
Packaging	15 m rolls. 30 m rolls.	
Storage/Shelf Life	60 months from date of production if stored in unopened, undamaged and sealed original packaging, in dry conditions at temperatures not exceeding +30°C. Protect from UV light.	
Technical Data		
Density	1.4 ± 0.1 kg/l	
Chemical Base	Polyvinyl Chloride	
Service Temperature	- 35°C to + 55°C	
Tensile Strength	<ul style="list-style-type: none"> ≥ 10 N/mm² ≥ 12.17 N/mm² ≥ 11 N/mm² 	DIN 53455 CRD-C 573, ASTM D412 BS 2782 M320A
Tear Strength	≥ 12 N/mm ²	DIN 53507 A
Shore A Hardness	70 ± 5	DIN 53505
Elongation at Break	<ul style="list-style-type: none"> > 300 % > 300 % > 300 % 	DIN 53455 CRD-C 573, ASTM D412 BS 2782 M320A
Chemical Resistance	Permanent: Water, seawater, sewage, road salt solutions. Temporarily: Diluted inorganic alkalis, mineral acids and mineral oils.	
Alkali Resistance	Passed.	CRD-C 572-65
Application Details		
Welding Temperature	~ 200°C.	



Construction

Forms		Type	Width (cm)	Roll Length (m)	Nom Thickness (mm (±10%))	Max. Water head (m)	
Centrally Placed Waterbars Installation in the center of concrete structure. Easy anchoring of waterbars to reinforcement with special fixing clips	Construction Joint						
	Light Profile						
		V-20L V-24L V-32L	20 24 32	30 30 15	4 4 4.5	10 15 25	
	Standard Profile						
		V-15E V-20E V-24E V-32E	15 20 24 32	30 30 30 15	5 6 6.5 7	5 15 25 30	
	Expansion Joint						
	Light Profile						
		O-20L O-25L O-32L	20 25 32	15 15 15	2.2 2.4 3	10 15 25	
	Standard Profile						
		O-20E O-25E O-32E	20 25 32	15 15 15	5 6 7	15 25 30	
		M-22 M-25 M-35	22 25 35	15 15 15	5 5 6	10 10 25	
	Surface Waterbars Installation on the surface of concrete structures	Construction Joint					
		AR-20* AR-25* AR-28 AR-31	20 25 28 31	15 15 15 15	3.5 3.5 3.5 4	5 10 15 15	
Expansion Joint							
		DR-21* DR-26* DR-29 DR-32	21 26 29 32	15 15 15 15	3.5 3.5 3.5 4	5 10 15 15	
Joint Finishing type Installation by pushing onto the formwork board of onto joint lining	Construction Joint						
		FA2-5 FA3-10 FA3-14	2/5 3/10 3/14	25 25 25	~3 ~5 ~5	0 5 5	

* only with four pins

Application


Selection

The selection of a suitable waterbar is governed by the type of joint, concrete thickness, grade of concrete, reinforcement position, expected movement (expansion/shear) as well as waterhead to which it is to be exposed to

General Guide lines:

Experience has shown that application of a few simple rules will ensure a satisfactory result:

- The overall width of the waterbar should be at little less or equal to the thickness of the concrete slab into which it is placed.
- The overall width of the waterbar should be at least six times the size of the largest aggregate used.
- For optimum results, centrally placed waterbars are preferred



Installation/Fixation

Centrally Placed Waterbars:

Installation in the centre of the concrete structures. Easy anchoring of Sika Waterbars to reinforcement with special fixing clips (5 pieces per m).

Surface Waterbars


Installation on the surface of the formwork or on the surface of the base/drylean concrete.

Joint Finishing Types


Installation by pushing onto the formwork or onto the joint lining.

Proper fixing of the waterbars to the reinforcement (or formwork) is essential, as are the careful pouring and compaction of the concrete. Fixing clips for internally placed waterbars are available.


Fixing




Centrally placed types




Externally paced types
FA - types



Compaction



Wrong



Correct

Welding Waterbars

Sika Waterbars® are made from virgin thermoplastic PVC and can therefore be welded easily. The ends are secured in a welding jig (available for each type) and heated with suitable welding equipment (also available), until an even, molten bead of PVC appears. The welding equipment is then removed and the molten ends pressed together firmly.

Junction Pieces

Junction pieces can easily be manufactured on site. However, a wide range of standardized, factory made junction pieces, are available. All having a 30 cm free wing allowing easy butt-welding at site. For non standard junction pieces drawings must be provided, giving exact details required.

Material requirement and number and type of welding.

Type	Material*	Welding – type
Cross-piece flat	1.20 m + 2.0 x width	2 mitre-weldings
Cross-piece Vertical	1.20 m	2 butt-weldings
T-piece flat	0.90 m + 1.5 x width	1 mitre-welding
T-piece Vertical	0.09 m	1 butt-welding
L-piece flat	0.60 m + 2.0 x width	1 mitre-welding
Comer-piece Vertical	0.60 m,	1 butt-welding

* Free Wing: 30 cm (all)

Notes


- In case of negative water pressure surface waterbars cannot be used.
- All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control

Protective Measures

Use personal protective clothing. Change soiled work clothes and wash hands before breaks and after finishing work. Welding must only take place at well ventilated areas or while wearing an oxygen-mask.

Legal notes

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Egypt for Construction Chemicals
 El About City
 1st industrial zone (A)
 Section # 10 Block 13035,
 Egypt

Tel :+202- 6100714/15/16/17/18
 Fax :+202- 6100759
 Mob :+2012- 3908822/55
 www.sika.com.eg

