

## Sikafloor®-356 N

### 2-Part PUR Transparent Matt Seal Coat

**Product Description** Sikafloor®-356 N is a two part tough elastic, transparent, solvent containing, polyurethane resin, matt seal coat. Suitable for use in hot and tropical climates.

**Uses**

- Matt sealer for Sikafloor® smooth epoxy coatings
- Matt finish for Sikafloor® broadcast and sealed screeds in dry processing areas

**Characteristics / Advantages**

- UV-resistant
- Tough-elastic
- Good mechanical and chemical resistance
- Non-yellowing
- Easy application

#### Test

**Approval / Standards** Conforms to the requirements for decontamination ability (according to BS 4247, IRAS Ltd., St. Hellens, UK and to DIN 25 415-1 Test report 4301699wü2, Forschungszentrum Jülich, Apr. 2000.

#### Product Data

**Form** Liquid

**Appearance / Colours** Resin - part A: transparent  
Hardener - part B: transparent

**Packaging** Part A: 8.0 kg  
Part B: 2.0 kg  
Part A+B: 10 kg unipacks

**Storage Conditions / Shelf Life** 6 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

#### Technical Data

**Chemical Base** Polyurethane

**Density (at +23°C)** Part A: ~ 1.13 kg/l  
Part B: ~ 0.89 kg/l  
Mixed Resin: ~ 0.97 kg/l (DIN EN ISO 2811-1)



## System Information

### System Structure

Seal coat of smooth EP coatings:  
Base coat: Sikafloor®-261 or -162  
Matt seal coat: 1 x **Sikafloor®-356 N**

Matt finish for sealed broadcast coatings in dry processing areas:  
Base coat: e.g. Sikafloor®-261 + quartz sand  
Seal coat: Sikafloor®-261 or -162  
Matt seal coat: 1 x **Sikafloor®-356 N**

## Application Details

### Consumption / Dosage

Coating System	Product	Consumption
Seal coat for smooth coatings	<b>Sikafloor®-356 N</b>	0.10 - 0.15 kg/m <sup>2</sup>
Finishing of sealed broadcast coatings	<b>Sikafloor®-356 N</b>	0.15 - 0.30 kg/m <sup>2</sup>

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

### Substrate Quality

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.  
If in doubt, apply a test area first.

### Substrate Preparation

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

### Application Conditions / Limitations

#### Substrate Temperature

+10°C min. / +30°C max.

#### Ambient Temperature

+10°C min. / +30°C max.

#### Relative Air Humidity

80% r.h. max.

#### Dew Point

Beware of condensation!  
The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

## Application Instructions

### Mixing

Part A : part B = 80 : 20 (by weight)

### Mixing Time

Prior to mixing stir part A mechanically. When all of part B has been added to part A continuously mix for 3 minutes until a uniform mix has been achieved.  
To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix.  
Over mixing must be avoided to reduce air entrainment.

### Mixing Tools

**Sikafloor®-356 N** must be mechanically mixed using an electric power stirrer (300 - 400 rpm) or other suitable equipment.

### Application Method / Tools

Prior to application, confirm r.h. and dew point.  
*Seal coat / matt finish:*  
Uniformly spread **Sikafloor®-356 N** using a short pile nylon roller.  
A seamless finish can be achieved if a "wet" edge is maintained during application.

### Cleaning of Tools

Clean all tools with Thinner C immediately after use. Hardened / cured material can only be removed mechanically.

## Potlife

Temperature	Time
+10°C	~ 120 minutes
+20°C	~ 60 minutes
+30°C	~ 20 minutes

## Waiting Time / Overcoatability

Before applying **Sikafloor®-356 N** on Sikafloor®-162 / -261 allow:

Substrate temperature	Minimum	Maximum
+10°C	48 hours	4 days
+20°C	24 hours	3 days
+30°C	18 hours	2 days

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

## Notes on Application / Limitations

Freshly applied **Sikafloor®-356 N** must be protected from damp, condensation and water for at least 24 hours.

Uncured material reacts in contact with water (foaming). During application care must be taken that no sweat drops into fresh **Sikafloor®-356 N** (wear head and wrist bands)

Apply **Sikafloor®-356 N** to tack free Sikafloor®-261 or -162

Unevenness of the substrate and inclusions of dirt cannot be covered by thin sealer coats. Therefore the substrate and adjacent areas must be cleaned thoroughly prior to application.

### Tools

Recommended Supplier of Tools:

PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, [www.polyplan.com](http://www.polyplan.com)

## Curing Details

### Applied Product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 36 hours	~ 5 days	~ 10 days
+20°C	~ 24 hours	~ 3 days	~ 7 days
+30°C	~ 16 hours	~ 2 days	~ 3 days

Note: Times are approximate and will be affected by changing ambient conditions

## Cleaning / Maintenance

### Methods

To maintain the appearance of the floor after application, **Sikafloor®-356 N** must have all spillages removed immediately and be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc using suitable detergents and waxes.

### Notes

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Local Restriction

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## EU Regulation 2004/42 VOC - Decopaint Directive.

According to the EU-Directive 2004/42, the maximum allowed content of VOC Product category IIA / j Type **sb**) is 550 / 500 g/l (Limits 2007 / 2010), for the ready to use product.

The maximum content of **Sikafloor®-356 N** is < 500 g/l VOC for the ready to use product.

## Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request



**Sika Gulf B.S.C (c)**  
Bldg. 925, Road 115, Sitra Area 601  
P.O. Box 15776  
Adliya, Kingdom of Bahrain  
TEL: +973 17738 188  
Fax: +973 17732 476  
E-mail: [sika.gulf@bh.sika.com](mailto:sika.gulf@bh.sika.com)  
Web: <http://www.sika.com.bh>

