

Sikafloor®-410

1-Part PUR Elastic Matt Seal Coat

Product Description Sikafloor®-410 is a one part, elastic, solvent containing, UV resistant, moisture curing polyurethane resin based matt seal coat.

Uses

- Abrasion resistant seal coat with crack-bridging properties
- Seal coat for Sikafloor®-400 N Elastic and Sikafloor®-400 N Elastic+
- Only for exterior application

Characteristics / Advantages

- Crack bridging elastic seal coat
- UV resistant, non-yellowing
- Abrasion resistant with normal use
- Slip resistant surfaces are possible
- Easy application

Product Data

Form Liquid

Appearance / Colour Transparent

Packaging 3 litres and 10 litres units

Storage

Storage Conditions / Shelf Life 6 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

Technical Data

Chemical Base Polyurethane

Density (at +23°C) Resin: ~ 1.0 kg/lt (DIN EN ISO 2811-1)

Solid Content ~ 45% (by volume) / ~ 50% (by weight)

Mechanical / Physical Properties

Tensile Strength ~ 27 N/mm² (14 days / +23°C) (DIN 53505)

Elongation at Break ~ 300% (14 days / +23°C) (DIN 53504)



Resistance

Chemical Resistance Resistant against many chemicals. Please ask for a detailed chemical resistance table.

Thermal Resistance

Exposure*	Dry heat
Permanent	+50°C

*No simultaneous chemical and mechanical exposure.

System Information

System Structure

Seal coat for smooth coatings:

Coating: Sikafloor®-400 N Elastic / Sikafloor®-400 N Elastic+
Seal coat: 1 x **Sikafloor®-410**

Seal coat for broadcast systems:

Coating: Sikafloor®-400 N Elastic / Sikafloor®-400 N Elastic+,
broadcast to excess with quartz sand or coloured chips
Seal coat: 2 x **Sikafloor®-410**

Slip resistant seal coat:

Coating: Sikafloor®-400 N Elastic / Sikafloor®-400 N Elastic+
Seal coat: **Sikafloor®-410** + quartz sand 0.1 - 0.3 mm

Application Details

Consumption / Dosage

Coating System	Product	Consumption
Matt seal coat for smooth coatings of Sikafloor®-400 N Elastic / Elastic+	Sikafloor®-410	~ 0.15 kg/m ²
Matt seal coat for broadcast coatings Sikafloor®-400 N Elastic / Elastic+	2 x Sikafloor®-410	0.3 - 0.5 kg/m ²
Slip resistant seal coat	Sikafloor®-410 + 3-5 wt.-% quartz sand 0.1 - 0.3 mm	~ 0.15 kg/m ²

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

Substrate Quality

The Sikafloor® substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc..
Pull-off strength must be not less than 1.5 N/mm²
If in doubt, apply a test area first.

Substrate Preparation

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Application Conditions / Limitations

Substrate Temperature +10°C min. / +30°C max.

Ambient Temperature +10°C min. / +30°C max.

Relative Air Humidity 80% r.h. max.
35% min. (below +20°C: 45% min.)

Dew Point

Beware of condensation!
The substrate and uncured floor must be at least 3°C above the dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing Time Prior to use stir **Sikafloor®-410** mechanically for 3 minutes.
If the addition of quartz sand is required it must be added into the **Sikafloor®-410** until a uniform mix has been achieved.
Over mixing must be avoided to minimize air entrapment.

Mixing Tools **Sikafloor®-410** must be mechanically mixed using an electric power stirrer (300 - 400 rpm) or other suitable equipment.

Application Method / Tools Prior to application, confirm substrate moisture content, r.h. and dew point.
Sealer coat:
Uniformly spread **Sikafloor®-410** using a short pile nylon roller.
A seamless finish can be achieved if a 'wet' edge is maintained during application.

Cleaning of Tools Clean all tools and application equipment with Thinner C immediately after use.
Hardened / cured material can only be mechanically removed.

Potlife The material in opened containers should be applied immediately. With open containers surface film formation will happen within 1 - 2 hours.
High temperatures and high air humidity will accelerate curing significantly.

Waiting Time / Overcoatability Before applying **Sikafloor®-410** on Sikafloor®-400 Elastic / Sikafloor®-400 Elastic+ allow:

Substrate temperature	Minimum	Maximum
+10°C	24 hours	5 days
+20°C	8 hours	3 days
+30°C	5 hours	2 days

Before applying **Sikafloor®-410** on **Sikafloor®-410** allow:

Substrate temperature	Minimum	Maximum
+10°C	24 hours	5 days
+20°C	8 hours	3 days
+30°C	5 hours	2 days

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Notes on Application / Limitations Do not use for interior applications.
Freshly applied **Sikafloor®-410** must be protected from damp, condensation and water for at least 24 hours (+20°C).
Unevenness of substrates as well as inclusions of dirt cannot be covered by thin sealer coats. Therefore substrates and adjacent areas must be cleaned thoroughly prior to application.

Tools

Recommended Supplier of Tools:

PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, www.polyplan.com

Curing Details

Applied Product ready for use

Temperature	Rain resistant	Foot traffic	Full Cure
+10°C	~ 15 hours	~ 24 hours	~ 7 days
+20°C	~ 5 hours	~ 8 hours	~ 5 days
+30°C	~ 3 hours	~ 5 hours	~ 4 days

Note: Times are approximate and will be affected by changing ambient conditions.

Cleaning / Maintenance

Methods To maintain the appearance of the floor after application, **Sikafloor®-410** must have all spillages removed immediately and be regularly cleaned using rotary brushes, mechanical scrubbers, scrubber dryers, high pressure washers, wash and vacuum techniques etc using suitable detergents and waxes.

Notes All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

EU Regulation 2004/42 VOC - Decopaint Directive According to the EU-Directive 2004/42, the maximum allowed content of VOC Product category IIA / i Type **sb**) is 600 / 500 g/l (Limits 2007 / 2010), for the ready to use product.

The maximum content of **Sikafloor®-410** is < 500 g/l VOC for the ready to use product.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request



Sika Gulf B.S.C (c)
 Bldg. 925, Road 115, Sitra Area 601
 P.O. Box 15776
 Adliya, Kingdom of Bahrain
 TEL: +973 17738 188
 Fax: +973 17732 476
 E-mail: sika.gulf@bh.sika.com
 Web: <http://www.sika.com.bh>

