

Sikafloor®-264

2-part epoxy roller and seal coat

Product Description

Sikafloor®-264 is a two part, economic, solvent-free coloured epoxy resin, suitable for use under hot climate condition.

“Solvent free according to German recommendation DEUTSCHE BAUCHEMIE^{EV}”

Uses

- Roller coat for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages, loading ramps and car parks
- Seal coat for broadcast systems.

Characteristics / Advantages

- Good chemical and mechanical resistance
- Easy application
- Economical
- Liquid proof
- Solvent-free
- Gloss finish
- Slip resistant surface possible
- Seamless floor finish
- Texture finish possible
- Easy to clean and maintain

Product Data

Form

Appearance / Colours

Resin - part A: coloured, liquid
Hardener - part B: transparent, liquid

Standard colour range
RAL 3011/ 6029/ 7030/ 7032/ 7035/ 7045
Other colours on request.

Under direct sun light there may be some discolouration and colour variation; this has no influence on the function and performance of the coating.

Packaging

Part A: 15.8 kg
Part B: 4.20 kg
Part A+B: 20 kg ready to mix unit

Part A: 220 kg drums
Part B: 177 kg, 59kg drums
Part A+B: 1 Drum Part A (220 kg) + 1 drum Part B (59 kg) = 279 kg
3 Drums Part A (220 kg) + 1 Drum Part B (177 kg) = 837 kg



Storage

Storage Conditions / Shelf-Life	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.
--	---

Technical Data

Chemical Base	Epoxy	
Density	Part A: ~ 1.64 kg/l Part B: ~ 1.00 kg/l Mixed resin: ~ 1.40 kg/l All Density values at +23°C.	(DIN EN ISO 2811-1)
Solid Content	~ 100% (by volume) / ~ 100% (by weight)	

Mechanical / Physical Properties

Compressive Strength	Resin: ~ 60 N/mm ² (28 days / +23°C)	(EN 196-1)
Flexural Strength	Resin: ~ 30 N/mm ² (28 days / +23°C)	(EN 196-1)
Bond Strength	> 1.5 N/mm ² (failure in concrete)	(ISO 4624)
Shore D Hardness	76 (7 days / +23°C)	(DIN 53 505)
Abrasion Resistance	70 mg (CS 10/1000/1000) (8 days / +23°C)	(DIN 53 109 (Taber Abrader Test))

Resistance

Chemical Resistance Resistant to many chemicals. Please ask for a detailed chemical resistance table.

Thermal Resistance

Exposure*	Dry heat
Permanent	+50°C
Short-term max. 7 d	+80°C
Short-term max. 12 h	+100°C

Short-term moist/wet heat* up to +80°C where exposure is only occasional (steam cleaning etc.)

*No simultaneous chemical and mechanical exposure.

System Information

System Structure

Roller coating:

Primer: 1 x Sikafloor®-161 (optional)
Coating: 2 x Sikafloor®-264

Textured roller coating:

Primer: 1 x Sikafloor®-161 (optional)
Coating: 1 - 2 x Sikafloor®-264 + Extender T

Textured roller coating with improved slip resistance:

Primer: 1 x Sikafloor®-161 (optional)
Coating: 1 x Sikafloor®-264 + Extender T + quartz sand (0.1 - 0.5 mm)

Note: In cases of limited exposure and normal absorbent concrete substrates priming with Sikafloor®-161 is not necessary.

Broadcast system approx. 4 mm:

Primer*: 1 x Sikafloor®-161
Base coat: 1 x Sikafloor®-263 SL + quartz sand (0.1 - 0.3 mm)
Broadcasting: quartz sand (0.4 - 0.7 mm) broadcast to excess
Seal coat: 1 x Sikafloor®-264

Application Details

Consumption / Dosage

Coating System	Product	Consumption
Primer	Sikafloor® -161	0.15 - 0.40 kg/m ²
Levelling (optional)	Sikafloor®-161 levelling mortar	Refer to PDS of Sikafloor®-161
Roller coating	2 x Sikafloor® -264	0.15 - 0.3 kg/m ² for each layer
Textured roller coating	1 - 2 x Sikafloor®-264 + Extender T	0.4 - 0.8 kg/m ² per layer
Textured roller coating with improved slip resistance	10 pbw Sikafloor®-264 + Extender T + 1 pbw quartz sand (0.1 - 0.5 mm)	0.5 - 0.8 kg/m ² 0.05 - 0.07 kg/m ²
Broadcast system (Film thickness ~ 4.0 mm)	1 pbw Sikafloor®-263 SL 1 pbw quartz sand (0.1 - 0.3 mm) + broadcasting quartz sand 0.4 -0.7 mm + Seal coat Sikafloor® -264	2.00 kg/m ² 2.0 kg/m ² ~ 6.0 kg/m ² ~ 0.7 kg/m ²

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.

Substrate Quality

The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.

If in doubt, apply a test area first.

Substrate Preparation

Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.

Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.

Repairs to the substrate, filling of blowholes/voids and surface levelling can be carried out using appropriate products from the Sikafloor®, SikaDur® and SikaGard® range of materials.

The concrete or screed substrate has to be primed or levelled in order to achieve an even surface.

High spots must be removed by e.g. grinding.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Application Conditions / Limitations

Substrate Temperature

+ 10°C min. / 35°C max.

For Substrate temperature greater than 35°C please consult our technical department.

Ambient Temperature

+ 10°C min. / 35°C max.

For Ambient temperature greater than 35°C please consult our technical department.

Substrate Moisture Content

≤ 4% pbw moisture content.

Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method.

No rising moisture according to ASTM (Polyethylene-sheet).

Relative Air Humidity

80% r.h. max.

Dew Point

Beware of condensation!

The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing	Part A : part B = 79 : 21 (by weight)
Mixing Time	<p>Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 2 minutes until a uniform mix has been achieved.</p> <p>To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix.</p> <p>Over mixing must be avoided to minimise air entrainment.</p>
Mixing Tools	Sikafloor®-264 must be thoroughly mixed using a low speed stirrer (300 - 400 rpm) or other suitable equipment.
Application Method / Tools	<p>Prior to application, confirm substrate moisture content, r.h. and dew point. If > 4% pbw moisture content, Sikafloor® EpoCem® may be applied as a T.M.B. (temporary moisture barrier) system.</p> <p><i>Levelling:</i> Rough surfaces need to be levelled first. Therefore use e.g. Sikafloor®-161 levelling mortar (see PDS).</p> <p><i>Coating:</i> Sikafloor®-264 as coating, can be applied by short-piled roller (crosswise).</p> <p><i>Seal coat:</i> Sealer coats can be applied by squeegee and then back-rolled (crosswise) with a short-piled roller.</p>
Cleaning of Tools	Clean all tools and application equipment with Sika Thinner immediately after use. Hardened and/or cured material can only be removed mechanically.

Potlife

Temperatures	Time
+10°C	~ 50 minutes
+20°C	~ 25 minutes
+30°C	~ 15 minutes

Waiting Time / Overcoating

Before applying Sikafloor®-264 on Sikafloor®-161 allow:

Substrate temperature	Minimum	Maximum
+10°C	24 hours	3 days
+20°C	12 hours	2 days
+30°C	8 hours	1 day

Before applying Sikafloor®-264 on Sikafloor®-263 SL allow:

Substrate temperature	Minimum	Maximum
+10°C	30 hours	3 days
+20°C	24 hours	2 days
+30°C	16 hours	1 day

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Notes on Application / Limitations

Do not apply Sikafloor®-264 on substrates with rising moisture.

Do not blind the primer.

Freshly applied Sikafloor®-264 must be protected from damp, condensation and water for at least 24 hours.

Avoid puddles on the surface with the primer.

For areas with limited exposure and normally absorbent concrete substrates priming with Sikafloor®-161 is not necessary for roller or textured coating systems.

For roller / textured coatings: Uneven substrates as well as inclusions of dirt cannot and should not be covered by thin sealer coats. Therefore both substrate and adjacent areas must always be prepared and cleaned thoroughly prior to application.

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

For exact colour matching, ensure the Sikafloor®-264 in each area is applied from the same control batch numbers.

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

Curing Details

Applied Product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 72 hours	~ 6 days	~ 10 days
+20°C	~ 24 hours	~ 4 days	~ 7 days
+30°C	~ 18 hours	~ 2 days	~ 5 days

Note: Times are approximate and will be affected by changing ambient conditions.

Cleaning / Maintenance

Methods

To maintain the appearance of the floor after application, Sikafloor®-264 must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Construction



Sika Gulf BSC
Bldg. 925, Road 115,
Sitra Area 601.
P.O. Box 15776
Adliya, Kingdom of Bahrain

Tel: +973 17 738 188
Fax: +973 17 732 476
e-mail: sika.gulf@bh.sika.com
Web: <http://www.sika.com.bh>

